T-J305 6V 330Ah

Sealed Lead-Acid (SLA) Deep Cycle Battery



Applications

- EV Golf Cart, Utility Vehicles or NEV
- Scissor Lifts, Aerial Work Platforms
- Floor Sweeper, Scrubbers or Floor Cleaning Machine
- Material Handling
- Renewable Energy System
- Engine Starting

General Features

- DOD 50% more than 1,200 life cycles
- Long life and high stability under high temperature environment
- Design for usable at tropical countries
- Rechargeable and maintenance-free
- Gel VRLA (Valved Regulated Lead-Acid) battery

Specifications

BCI Group Size	Model	Voltage	Cell	[1] Capacity (Ah) @ 25°C						[2] Minutes of Discharge			Internal Resistance	[3] CCA	Dimensions (mm)				Weight (kg)
				1 hr rate	2 hr rate	5 hr rate	10 hr rate	20 hr rate	100 hr rate	@25A	@56A	@75A			L	W	H	TH	
902	T-J305	6V	3	173	220	262	309	330	374	700	278	192	≤ 2.5mΩ	1,100	295	178	354	360	46.5

[1] The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate a 25ºC and maintain a voltage above 1.75V/cell. Capacities are based on peak performance.
[2] The number of minutes a battery can deliver when discharged at a constant rate at 25ºC and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
[3] CCA (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.

Charging Instructions


Recommended Charge Current	**Cyclic Application**
- With Temperature Compensation	66.0 A Max.
- Without Temperature Compensation	33.0 - 66.0 A
Charge Voltage (6 Volts)	7.2 - 7.35 V
Bulk Charge	7.30 V
Absorption Charge	7.30 V
Float Charge	6.85 V
Temperature Compensate Factor	- 4 mV/°C/Cell

DO NOT charge at temperature corrected voltages above 7.5 Volts (2.5 Volts/cell).
Use of voltage controlled charger is a requirement for warranty coverage.
For best cycle llfe, limit discharge to less than 50% of the battery's 20 hour capacity.

Operating Temperature

Discharge:	-15°C~45°C
Charge:	-15°C~45°C
Storage:	-15°C~45°C

Dimensions and Terminal




T-J305 6V 330Ah

Sealed Lead-Acid (SLA) Deep Cycle Battery


Battery Construction

Positive plate	Negative plate	Container&Cover	Safety valve	Terminal	Seperator	Electrolyte	Pillar seal
Thick high Sn, low Ca grid	Pb-Ca grid	ABS	Si-Rubber	Copper insert M8	PVC/AGM seperator for high pressure cell	Silica Gel	Two layers epoxy resin seal

Charging characteristics




Discharge characteristics (25°C)



Cycle life vs. Depth of discharge (25°C)



Temperature effect on capacity



DENA ENGINEERING CO.,LTD.

185/1 Wongsawang Road, Wongsawang, Bangsue, Bangkok 10800 THAILAND

Tel. 02-587-7780, 02-910-9600 e-mail: dena@dena.co.th www.dena.co.th